



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷: C08J 3/20, C08K 9/04, 9/08	A1	(11) International Publication Number: WO 00/29467 (43) International Publication Date: 25 May 2000 (25.05.00)
(21) International Application Number: PCT/US99/25974 (22) International Filing Date: 4 November 1999 (04.11.99) (30) Priority Data: 60/107,235 5 November 1998 (05.11.98) US 60/108,979 18 November 1998 (18.11.98) US (71) Applicant (for all designated States except US): THE DOW CHEMICAL COMPANY [US/US]; 2030 Dow Center, Midland, MI 48674 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): CHOU, Chai-Jing [US/US]; 1422 Bluestone Drive, Missouri City, TX 77549 (US). GARCIA-MEITIN, Eddy, I. [US/US]; 36 Colony Square, Angleton, TX 77515 (US). (74) Agent: STEVENS, Timothy, S.; Patent Department, 2030 Dow Center, Midland, MI 48674 (US).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: NANOCOMPOSITE		
(57) Abstract <p>The instant invention in one embodiment is a process for producing a nanocomposite polymer by dispersing a polyvalent anionic organic edge coated quaternary ammonium intercalated multi-layered silicate material into a thermoplastic polymer. The process includes the step of mixing the polyvalent anionic polymer edge coated quaternary ammonium intercalated multi-layered silicate material with the thermoplastic polymer at a temperature greater than the melting or softening point of the thermoplastic polymer. The instant invention in another embodiment is a process for producing a nanocomposite polymer by dispersing a polyvalent anionic organic edge coated quaternary ammonium intercalated multi-layered silicate material into a thermoset polymer. The process of this embodiment includes the steps of: (a) mixing the polyvalent anionic organic edge coated quaternary ammonium intercalated multi-layered silicate material with a thermoset prepolymer; and (b) curing the thermoset prepolymer to set the thermoset polymer. The instant invention in yet another embodiment is a composition including (a) a polymer; and (b) a multi-layered silicate material dispersed in the polymer, the multi-layered silicate material having edges, at least a portion of the edges of the multi-layered silicate material being bound to a polyvalent anionic organic material. The instant invention in further yet another embodiment is a process for producing a nanocomposite polymer, including the steps of: (a) mixing a polyvalent anionic organic edge coated quaternary ammonium intercalated multi-layered silicate material with a monomer; and (b) polymerizing the monomer.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

INTERNATIONAL SEARCH REPORT

Patent Application No

PCT/US 99/25974

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08J3/20 C08K9/04 C08K9/08

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08J C08K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 558 075 A (SUSS NAOMI R ET AL) 10 December 1985 (1985-12-10) claims 1,2	10, 12, 13
A	WO 93 04117 A (ALLIED SIGNAL INC) 4 March 1993 (1993-03-04) claim 10	1
A	EP 0 459 472 A (TOYODA CHUO KENKYUSHO KK) 4 December 1991 (1991-12-04) claims 8-11	16-18



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubt on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

29 March 2000

Date of mailing of the international search report

06/04/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3018

Authorized officer

Siemens, T

INTERNATIONAL SEARCH REPORT

Information on patent family members

Internal Application No

PCT/US 99/25974

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4558075	A	10-12-1985	NONE	
WO 9304117	A	04-03-1993	AT 159270 T	15-11-1997
			CA 2115255 A	04-03-1993
			DE 69222773 D	20-11-1997
			DE 69222773 T	12-02-1998
			EP 0598836 A	01-06-1994
			JP 2674720 B	12-11-1997
			JP 6504810 T	02-06-1994
			WO 9304118 A	04-03-1993
			US 5747560 A	05-05-1998
EP 0459472	A	04-12-1991	JP 2872756 B	24-03-1999
			JP 4033955 A	05-02-1992
			DE 69111696 D	07-09-1995
			DE 69111696 T	25-01-1996
			US 5164460 A	17-11-1992

NANOCOMPOSITE

This invention relates to polymers reinforced with delaminated or exfoliated multi-layered silicates, that is, nanocomposite polymers.

Nanocomposite polymers are compositions comprising a relatively high number
5 (but relatively low weight) of preferably single layers of exfoliated silicate material dispersed in a given volume of continuous polymer matrix. United States Patent 5,717,000 to Seema V. Karande, Chai-Jing Chou, Jitka H. Solc and Kyung W. Suh, and United States Patent Application Serial Number 034,620 filed December 31, 1996. As discussed in the '000 patent and as is well known in the art, nanocomposite polymers exhibit many increased physical
10 property enhancements at a much lower weight percent of filler than conventionally filled polymers. Other United States Patents disclosing nanocomposites include 4,810,734 and 3,516,959. Edge coating of multi-layer silicate material is known, see United States Patent 4,434,075.

However, it can be difficult to get the multi-layer silicate material to exfoliate
15 into the polymer.

The instant invention is a solution, at least in part, to the above stated problem. In one embodiment, the instant invention is a process for producing a nanocomposite polymer by dispersing a polyvalent anionic organic edge coated quaternary ammonium intercalated multi-layered silicate material into a thermoplastic polymer. The
20 process comprises the step of: mixing the polyvalent anionic polymer edge coated quaternary ammonium intercalated multi-layered silicate material with the thermoplastic polymer at a temperature greater than the melting or softening point of the thermoplastic polymer.

The instant invention in another embodiment is a process for producing a
25 nanocomposite polymer by dispersing a polyvalent anionic organic edge coated quaternary ammonium intercalated multi-layered silicate material into a thermoset polymer. The process of this embodiment comprises the steps of: (a) mixing the polyvalent anionic organic edge coated quaternary ammonium intercalated multi-layered silicate material with a thermoset prepolymer; and (b) curing the thermoset prepolymer to set the thermoset polymer.

30 The instant invention in yet another embodiment is a composition comprising: (a) a polymer; and (b) a multi-layered silicate material dispersed in the polymer, the multi-layered silicate material having edges, at least a portion of the edges of the multi-layered silicate material being bound to a polyvalent anionic organic material.

The instant invention in further yet another embodiment is process for

producing a nanocomposite polymer, comprising the steps of: (a) mixing a polyvalent anionic organic edge coated quaternary ammonium intercalated multi-layered silicate material with a monomer; and (b) polymerizing the monomer.

Montmorillonite clay (a multi-layered silicate material) is stirred in water with an
5 excess of 3,400 molecular weight sodium polyacrylate (a polyvalent anionic copolymer of
mole ration 1:1 of ethylene and acrylic acid) available from the Rhone-Poulenc Company to
edge treat the clay. The edge treated clay is then stirred with an excess of a mixed
quaternary ammonium compound (68 percent bis hydroxyethyl, dodecyl, methyl-quaternary
10 ammonium compound and 32 percent bis hydroxy C-6 to C-9, dodecyl, methyl-quaternary
ammonium compound) to produce a polyacrylate edge coated quaternary ammonium
intercalated montmorillonite. The polyacrylate edge coated quaternary ammonium
intercalated montmorillonite is washed with water and dried. Ninety five parts of ethylene
adipate thermoplastic polyurethane (available from The Dow Chemical Company) is melted
(or softened) in a polymer mixer at 160 degrees Celsius at 200 rpm. Five parts of the dried
15 polyacrylate edge coated quaternary ammonium intercalated montmorillonite, as described
above in this paragraph, is added to the mixer and mixed for five minutes. Transmission light
microscopic examination of the product shows significantly fewer one hundred micrometer
sized clay clusters relative to the use of non-edge coated material. Transmission electron
microscopic examination of the product shows single and multiple layer exfoliation of the
20 silicate layers of the montmorillonite. The layers are counted in a representative view. Most
preferably, more of the layers are present as single layers than are present as multiple layers.
In any event the dispersion of the layers into the polymer is improved using the instant
invention relative to the use of a non-edge-coated material.

Polyvalent anionic organic materials are organic chemicals that have more than
25 one carboxylic acid or other anionic substituant such as a sulfonate or a phosphonate.
Preferably, the polyvalent anionic organic material is a polyvalent anionic polymer. Most
preferably, the polyvalent anionic organic material is polyacrylic acid. However, the specific
polyvalent anionic organic material used in the instant invention is not critical and can include,
without limitation thereto, for example, copolymers of styrene and acrylic acid or styrene and
30 sulfoethylmethacrylate.

The above referred to '000 patent and the '620 patent application list
exemplary multi-layered silicate materials required in the instant invention. For example, the
multi-layered silicate material can be, without limitation thereto: montmorillonite; nontronite;
beidellite; volkonskoite; hectorite saponite; sauconite; magadiite; medmontite; kenyaite;

laponite, mica, fluoromica and vermiculite. The above referred to '000 patent and '620 patent application also lists exemplary onium or quaternary ammonium compounds required in the instant invention. For example, the onium compound can be, without limitation thereto, quaternary ammonium compounds having octadecyl, hexadecyl, tetradecyl or dodecyl moieties. However, the specific multi-layered silicate material or onium compound used in the instant invention is not critical.

However, it should be understood that it is preferable to use polar substituted quaternary ammonium compounds with relatively polar polymers such as nylons and polyurethanes. Similarly, it is preferable to use non-polar substituted quaternary ammonium compounds with relatively non-polar polymers such as polypropylene and polyethylene. The terms "polar" and "non-polar" are used in their conventional sense. For example, a polar substituted quaternary ammonium compound is a quaternary ammonium compound having a hydroxy ethyl (C₂OH) or hydroxy hexyl (C₆OH) substituent(s).

The selection of a preferred quaternary ammonium compound is aided by comparing the electron photomicrographs of the nanocomposites made using the quaternary ammonium compounds being tested in the instant invention to determine which quaternary ammonium compound(s) give the greatest degree of exfoliation of the multi-layered silicate. Of course, physical property improvement of the nanocomposite v. the base polymer is the final objective of the instant invention but such improvement is often a function of the degree of exfoliation of the multi-layered silicate.

In addition to mixing the polyvalent anionic organic quaternary ammonium intercalated multi-layered silicate material with a molten thermoplastic polymer, the instant invention also includes mixing the polyvalent anionic organic quaternary ammonium intercalated multi-layered silicate material with a monomer(s) or thermoset prepolymer(s) followed by the polymerization of the monomer(s)/prepolymer(s).

1. A process for producing a nanocomposite polymer by dispersing a polyvalent anionic organic edge coated quaternary ammonium intercalated multi-layered silicate material into a thermoplastic polymer, the process comprising the step of: mixing the polyvalent anionic polymer edge coated quaternary ammonium intercalated multi-layered silicate material with the thermoplastic polymer at a temperature greater than the melting or softening point of the thermoplastic polymer.

2. The process of Claim 1, wherein the thermoplastic polymer is selected from the group consisting of a thermoplastic urethane, a thermoplastic epoxy, a thermoplastic polyester, a thermoplastic nylon, a thermoplastic polycarbonate; and blends thereof.

3. The process of Claim 1 or Claim 2, wherein the polyvalent anionic organic edge coated quaternary ammonium intercalated multi-layered silicate material exfoliates to produce single layers of silicate material and multiple layers of silicate material, the weight percent of the single layers of silicate material being greater than the weight percent of the multiple layers of silicate material.

4. The process of Claim 1 or Claim 3, wherein the thermoplastic polymer is a blend of thermoplastic polymers.

5. A process for producing a nanocomposite polymer by dispersing a polyvalent anionic organic edge coated quaternary ammonium intercalated multi-layered silicate material into a thermoset polymer, the process comprising the steps of:

(a) mixing the polyvalent anionic organic edge coated quaternary ammonium intercalated multi-layered silicate material with a thermoset prepolymer;

(b) curing the thermoset prepolymer to set the thermoset polymer.

6. The process of Claim 5, wherein the thermoset polymer is selected from the group consisting of a thermoset epoxy, a thermoset phenolic, a thermoset urethane, a thermoset rubber and blends thereof.

7. The process of Claim 5 or Claim 6, wherein the polyvalent anionic organic edge coated quaternary ammonium intercalated multi-layered silicate material exfoliates in step (a) to produce single layers of silicate material and multiple layers of silicate material, the weight percent of the single layers of silicate material being greater than the weight percent of the multiple layers of silicate material.

8. The process of Claim 5 or Claim 7, wherein the thermoset polymer is a blend of thermoset polymers.

9. The process of Claim 1, wherein the thermoplastic polymer is selected from the group consisting of polypropylene, polyethylene, polystyrene, polystyrene copolymers, acrylic polymers, acetyl polymers and thermoplastic elastomers and blends thereof.

10. A composition comprising:

(a) a polymer; and

(b) a multi-layered silicate material dispersed in the polymer, the multi-layered silicate material having edges, at least a portion of the edges of the multi-layered silicate material being bound to a polyvalent anionic organic material.

11. The composition of Claim 10, wherein at least about one half of the edges of the multi-layered silicate material are bound to the polyvalent anionic organic material.

12. The composition of Claim 10 or Claim 11, wherein the polymer is selected from the group of thermoplastic polymers and thermoset polymers and blends thereof.

13. The composition of Claim 12, wherein the thermoplastic polymers and thermoset polymers are selected from the group consisting of a thermoplastic urethane, a thermoplastic epoxy, a thermoplastic polyester, a thermoplastic nylon, a thermoplastic polycarbonate, polypropylene, polyethylene, polystyrene, polystyrene copolymers, acrylic polymers, acetyl polymers, thermoplastic elastomers, thermoset epoxy, a thermoset phenolic, a thermoset urethane, a thermoset rubber and blends thereof.

14. The process of Claims 1-9, wherein the polyvalent anionic organic is a polyacrylate.

15. The composition of Claims 10-13, wherein the polyvalent anionic organic is a polyacrylate.

16. A process for producing a nanocomposite polymer, comprising the steps of:

(a) mixing a polyvalent anionic organic edge coated quaternary ammonium intercalated multi-layered silicate material with a monomer; and

(b) polymerizing the monomer.

17. The process of Claim 16, wherein the monomer is a blend of monomers.

18. The process of Claim 16, wherein the polymer is selected from the group consisting of a thermoplastic urethane, a thermoplastic epoxy, a thermoplastic polyester, a thermoplastic nylon, a thermoplastic polycarbonate, polypropylene, polyethylene, polystyrene, polystyrene copolymers, acrylic polymers, acetyl polymers, thermoplastic elastomers,